

Product Texts

15% Glass Reinforced, Heat Stabilized, Extrusion Blow Molding

ISO 1043 PA6-I-GF15

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	40 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	21.6 / *	kg	-
^[C] Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5600 / 3000	MPa	ISO 527
^[C] Stress at break	110 / 60	MPa	ISO 527
^[C] Strain at break	5 / 15	%	ISO 527
^[C] Charpy impact strength, +23°C	80 / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	90 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	20 / 30	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10 / 10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	220 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	185 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	210 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	6.8 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2 / *	%	Sim. to ISO 62
^[C] Density	1200 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Blow Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

Asia Pacific

Other text information**Blow molding**[Blow Molding Recommendations for Akulon® K240-HPG3 & HPG3/A](#)