

Product Texts

15% glass fibre reinforced impact modified PA 6

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.004	mm/mm	ASTM D 955

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	5000 / 2600	MPa	ISO 527
^[C] Stress at break	100 / 60	MPa	ISO 527
^[C] Strain at break	5 / 15	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	56 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	16 / 24	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	7 / -	kJ/m ²	ISO 179/1eA
ASTM Data			
Tensile Strength at Break	91 / -	MPa	ASTM D 638
Elongation at Break	5 / -	%	ASTM D 638
Flexural Modulus	4068 / -	MPa	ASTM D 790
Flexural Strength	138 / -	MPa	ASTM D 790
Izod Impact notched, 1/8 in	171 / -	J/m	ASTM D 256

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	190 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	210 / *	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	205 / *	°C	ISO 306
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	3.0 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Burning rate, FMVSS, Thickness 1 mm	100	mm/min	ISO 3795 (FMVSS 302)
ASTM Data			
DTUL @ 66 psi	221	°C	ASTM D 648
DTUL @ 264 psi	204	°C	ASTM D 648

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / >1E15	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1200 / -	kg/m ³	ISO 1183
Density	1200	kg/m ³	ASTM D 792

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Viscosity number	145 / *	cm ³ /g	ISO 307, 1157, 1628

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	250 - 280	°C	-
Mold temperature	60 - 90	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Delivery form

Granules

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Additives

Release agent, Plasticizer

Other text information

Injection molding

PREPROCESSING; **Pretreatment**

Predrying: 4-6h / 80°C

PROCESSING ;Processing:

Melttemperature	250 - 280	°C
Mouldtemperature	60 - 90	°C