

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0095</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>80</b>	MPa	ASTM D 638
Flexural Modulus	<b>5500</b>	MPa	ASTM D 790
Flexural Strength	<b>115</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>60</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>220</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>130</b>	°C	ISO 75-1/-2

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1360</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>220 - 250</b>	°C	-
Mold temperature	<b>40 - 80</b>	°C	-

**Characteristics**

**Processing**

Injection Molding, Other Extrusion

**Regional Availability**

North America, Europe, South and Central America

**Delivery form**

Natural Color