

**Tarnamid® T-27 MT15**

PA6-MX15

Grupa Azoty S.A.

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt volume-flow rate, MVR	<b>70 / *</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>275 / *</b>	°C	-
Load	<b>5 / *</b>	kg	-
Molding shrinkage, parallel	<b>0.9 / *</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.0 / *</b>	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>5000 / 3500</b>	MPa	ISO 527
Tensile Strength	<b>75 / 50</b>	MPa	ISO 527
Strain at break	<b>7 / 10</b>	%	ISO 527
Flexural modulus, 23°C	<b>4200 / 2000</b>	MPa	ISO 178
Charpy impact strength, +23°C	<b>65 / 75</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>60 / 60</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>3.5 / 4</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	<b>3 / 3</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>5 / -</b>	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness	<b>60 / 90</b>	MPa	ISO 2039-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>221 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>90 / *</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>215 / *</b>	°C	ISO 306
Burning behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2 / *</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Relative permittivity, 1MHz	<b>3.9 / -</b>	-	IEC 62631-2-1
Dissipation factor, 1MHz	<b>700 / -</b>	E-4	IEC 62631-2-1
Volume resistivity	<b>1E10 / -</b>	Ohm*m	IEC 62631-3-1
Electric strength	<b>24 / -</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>600 / -</b>	-	IEC 60112
<b>Other properties</b>			
Density	<b>1240 / -</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Delivery form**

Granules, Black, Natural Color

**Special Characteristics**

U.V. stabilized or stable to weather, Heat stabilized or stable to heat

**Applications**

Automotive, Building Construction, Electrical and Electronical

**Regional Availability**

Europe