

ComAlloy E-10621

PA6-MX20

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	122	MPa	ASTM D 638
Flexural Modulus	8246	MPa	ASTM D 790
Flexural Strength	180	MPa	ASTM D 790
Izod Impact notched, 1/8 in	53.4	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	221	°C	ASTM D 648
DTUL @ 264 psi	199	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1480	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Regional Availability

North America