

**ComAlloy E-17221**

PA6-MX30

LyondellBasell Industries

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Break	<b>41</b>	MPa	ASTM D 638
Flexural Modulus	<b>3379</b>	MPa	ASTM D 790
Flexural Strength	<b>76</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>41.3</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>77</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1300</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America