

Denyl 6 3022

PA6-MX30

VAMP TECH SPA

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.01	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.01	mm/mm	ASTM D 955
Mechanical properties			
ISO Data			
Izod notched impact strength, +23°C	5	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	3500	MPa	ASTM D 638
Tensile Strength at Yield	55	MPa	ASTM D 638
Elongation at Break	5	%	ASTM D 638
Thermal properties			
ASTM Data			
DTUL @ 264 psi	65	°C	ASTM D 648
Vicat Temperature	195	°C	ASTM D 1525
Other properties			
Density	1380	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	3	h	-
Melt temperature	250	°C	-
Mold temperature	80	°C	-

Characteristics**Processing**

Injection Molding

Regional Availability

Europe