

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577
Molding shrinkage, normal	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3350	MPa	ISO 527
Stress at break	45	MPa	ISO 527
Strain at break	12	%	ISO 527

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	100	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1350	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Regional Availability

Europe

Applications

Automotive, Electrical and Electronical, Sports Equipment