

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	45 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	5200 / 2000	MPa	ISO 527
Tensile Strength	80 / 50	MPa	ISO 527
Strain at break	3 / 7	%	ISO 527
Flexural modulus, 23°C	3900 / 2000	MPa	ISO 178
Charpy notched impact strength, +23°C	5.3 / 25	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4 / -	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	210 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	60 / *	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
Electrical properties			
ISO Data			
Relative permittivity, 1MHz	3.8 / 6.2	-	IEC 62631-2-1
Dissipation factor, 1MHz	200 / 2000	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Comparative tracking index	500 / 500	-	IEC 60112
Other properties			
Water absorption	6.7 / *	%	Sim. to ISO 62
Humidity absorption	2.1 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m ³	ISO 1183
Material specific properties			
ISO Data			
Viscosity number	145 / *	cm ³ /g	ISO 307, 1157, 1628

Characteristics

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Features

Thermal Stability

Applications

Electrical and Electronical

Regional Availability

Europe