

Product Texts

Injection Molding, 67% Mineral Reinforced, Heat Stabilized, Thermal conductive material

ISO 1043 PA6-MX67

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8800 / 3000	MPa	ISO 527
^[C] Stress at break	90 / 55	MPa	ISO 527
^[C] Strain at break	3.5 / 13	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / 170	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	50 / 50	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	- / 10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	- / 10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	120 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	189 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	50 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	50 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Electric strength	33 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	2170 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Test specimen production	Value	Unit	Test Standard
ISO Data			
^[C] Injection Molding, melt temperature	290	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Melt temperature	280 - 300	°C	-
Mold temperature	80 - 120	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat, Thermally Conductive

Delivery form

Pellets

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information

Injection molding

PREPROCESSING

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 280 - 300 °C

Mold temperature: 80 - 120 °C