

**RESTRAMID B27 T20 BK 1A0010EX**

PA6-T20

Polimarky Spółka Jawna

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	5000 / -	MPa	ISO 527
Strain at break	4 / -	%	ISO 527

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	90 / *	°C	ISO 75-1/-2

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	1270 / -	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Black

**Regional Availability**

Europe