

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	6890	MPa	ASTM D 638
Tensile Strength at Break	103	MPa	ASTM D 638
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	6550	MPa	ASTM D 790
Flexural Strength	165	MPa	ASTM D 790
Izod Impact notched, 1/4 in	93	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	1570	kg/m ³	ASTM D 792

Characteristics

Delivery form
Pellets

Additives
Lubricants

Special Characteristics
Flame retardant

Applications
IT / Business Machine

Regional Availability
North America, Europe, Asia Pacific, South and Central America, Near East/Africa