

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	10300	MPa	ASTM D 638
Tensile Strength at Break	172	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	10300	MPa	ASTM D 790
Flexural Strength	221	MPa	ASTM D 790
Izod Impact notched, 1/4 in	240	J/m	ASTM D 256
Electrical properties			
ASTM Data			
Surface Resistivity	1000000	Ohm	ASTM D 257
Volume Resistivity	10000	Ohm*cm	ASTM D 257
Other properties			
Density	1320	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Applications

IT / Business Machine

Additives

Lubricants

Regional Availability

Europe, Asia Pacific, South and Central America, Near East/Africa