

Product Texts

Product-nomenclature: ISO 16396-PA610,GF30,M1HR,C22-090

Bio based Polyamide

Product Attributes

Improved impact resistance, Improved heat resistance, Improved UV resistance (outdoor use)

Markets

Automotive

Air intake systems, Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Cooling and climate control, Fuel systems, Powertrain and Chassis, Interior, Exterior

Electricals & Electronics

Electrical appliances, Electrical equipment, Connectors, Mobile phones and other portable devices, Lighting

Industry & Consumer goods

Housewares, Hydraulics & Pneumatics, Mechanical Engineering, Power transmission, Sports & Leisure, Tools & Accessories

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9000 / 7000	MPa	ISO 527
^[C] Stress at break	155 / 120	MPa	ISO 527
^[C] Strain at break	4 / 6	%	ISO 527
^[C] Charpy impact strength, +23°C	95 / 95	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	90 / 90	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	18 / 16	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	11 / 11	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	200 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 8.00 MPa	120 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	25 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	80 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E9 / 1E9	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E11	Ohm	IEC 62631-3-2
^[C] Electric strength	45 / 45	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	4 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1 / *	%	Sim. to ISO 62
^[C] Density	1310 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Granules, Black

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Certifications

Contains renewable resources

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa