

**NYLENE® 9110 G43**

PA610-GF43

Polymeric Resources Corporation

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>165</b>	MPa	ASTM D 638
Flexural Modulus	<b>10340</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>160</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>203</b>	°C	ASTM D 648
Melting Temperature	<b>221</b>	°C	ASTM D 3418

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1420</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>65 - 82</b>	°C	-
Pre-drying - Time	<b>2 - 4</b>	h	-
Processing humidity	<b>≤0.2</b>	%	-
Melt temperature	<b>287 - 316</b>	°C	-
Mold temperature	<b>82 - 93</b>	°C	-
Zone 1	<b>260 - 293</b>	°C	-
Zone 2	<b>277 - 299</b>	°C	-
Zone 3	<b>282 - 310</b>	°C	-
Nozzle temperature	<b>279 - 307</b>	°C	-
Injection pressure	<b>5 - 15</b>	MPa	-
Back pressure	<b>0 - 50</b>	MPa	-
Holding pressure	<b>4 - 12</b>	MPa	-
Maximum residence time	<b>6</b>	min	-

**Characteristics****Processing**

Injection Molding

**Features**

Copolymer

**Applications**

General Purpose

**Regional Availability**

North America