

NYLEM 66 GTF 45

PA66-(GF+T)25

Emas Plastik San.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.4	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	4250	MPa	ISO 527
Tensile Strength	125	MPa	ISO 527
Strain at break	3	%	ISO 527
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
Shore D hardness	78	-	ISO 7619-1

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	265	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	255	°C	ISO 75-1/-2
Vicat softening temperature, B	235	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1230	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 6	h	-
Melt temperature	260 - 300	°C	-
Mold temperature	80 - 100	°C	-

Characteristics**Processing**

Injection Molding, Other Extrusion

Regional Availability

Europe, Near East/Africa