

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	2120	MPa	ASTM D 638
Tensile Strength at Break	46	MPa	ASTM D 638
Elongation at Break	13.5	%	ASTM D 638
Flexural Modulus	2620	MPa	ASTM D 790
Flexural Strength	82	MPa	ASTM D 790
Izod Impact notched, 1/8 in	150	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1810	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 264 psi	73	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Surface Resistivity	1000000	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1150	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Regional Availability

Asia Pacific

### Special Characteristics

Increased electrical conductivity