

POLIMID LUB A 3020 GFTF

(PA66+PTFE)-GF30

Poliblend S.p.a.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.6	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7000	MPa	ISO 527
Stress at break	135	MPa	ISO 527
Strain at break	2	%	ISO 527
Izod impact strength, +23°C	45	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	8.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	250	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	265	°C	ISO 75-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Density	1480	kg/m ³	ISO 1183

Characteristics**Additives**

Lubricants

Regional Availability

Europe