

Product Texts

LNP THERMOCOMP RB006 compound is based on Nylon 6/6 resin containing 30% glass bead.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	2	mm/mm	ASTM D 955
Mold Shrinkage, TD	2	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7280	MPa	ISO 527
Stress at break	56	MPa	ISO 527
Strain at break	7.6	%	ISO 527
Flexural modulus	3840	MPa	ISO 178
Izod impact strength, +23°C, 4mm	25	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	3	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	6810	MPa	ASTM D 638
Tensile Strength at Break	58	MPa	ASTM D 638
Elongation at Break	6.5	%	ASTM D 638
Flexural Modulus	4050	MPa	ASTM D 790
Flexural Strength	124	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	390	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	95	°C	ISO 75-1/-2
ASTM Data			
Coefficient of Thermal Expansion, MD	63	E-6/K	ASTM D 696
Coefficient of Thermal Expansion, TD	61.9	E-6/K	ASTM D 696
DTUL @ 264 psi	92	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.72	%	Sim. to ISO 62
Density	1370	kg/m ³	ISO 1183
Water Absorption, 24hr	0.72	%	ASTM D 570
Density	1380	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America