

Titalon 7630TGF
(PA66+PTFE)-GF30

Titan Plastics Compounds Co., Ltd.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	130	MPa	ISO 527
Flexural modulus, 23°C	20000	MPa	ISO 178
Flexural strength	190	MPa	ISO 178
Charpy notched impact strength, +23°C	9	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Surface resistivity	1E14	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1680	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 100	°C	-
Pre-drying - Time	4	h	-
Melt temperature	260 - 290	°C	-
Mold temperature	60 - 100	°C	-

Characteristics

Processing

Injection Molding

Additives

Lubricants

Delivery form

Black

Regional Availability

Asia Pacific