

Product Texts

Product-nomenclature: ISO 16396-PA612-I,,EH,S18-020

Product Attributes

High viscosity, Hydrolysis resistant, Improved impact resistance, Improved heat resistance

Markets

Automotive

Air intake systems, Compressed air systems, Hydraulic systems, Automotive electr. and electronics, lighting, Cooling and climate control

Electricals & Electronics

Cables & Tubes

Industry & Consumer goods

Hydraulics & Pneumatics

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	3.0 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.4 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2000 / 1200	MPa	ISO 527
^[C] Yield stress	50 / 40	MPa	ISO 527
^[C] Yield strain	5 / 20	%	ISO 527
^[C] Nominal strain at break	>50 / >50	%	ISO 527
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	40 / 90	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	210 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	55 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	115 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	160 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E10 / 1E10	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E11	Ohm	IEC 62631-3-2
^[C] Electric strength	40 / 40	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	2.7 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.2 / *	%	Sim. to ISO 62
^[C] Density	1050 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Profile Extrusion, Other Extrusion

Delivery form

Granules, Black

Special Characteristics

Light stabilized or stable to light, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa