

Product Texts

Product-nomenclature: ISO 16396-PA612,,EH,S18-020

Product Attributes

High viscosity, Hydrolysis resistant, Improved alcohol resistance, Improved impact resistance, Improved heat resistance, Improved UV resistance (outdoor use)

Markets

Automotive

Air intake sytems, Compressed air systems, Hydraulic systems, Fuel systems

Electricals & Electronics

Cables & Tubes

Industry & Consumer goods

Hydraulics & Pneumatics

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	3.0 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.4 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	1800 / 1300	MPa	ISO 527
^[C] Yield stress	50 / 45	MPa	ISO 527
^[C] Yield strain	5 / 20	%	ISO 527
^[C] Nominal strain at break	>50 / >50	%	ISO 527
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	50 / 90	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	12 / 12	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	218 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	50 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	120 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	160 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	110 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E8 / 1E8	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
^[C] Electric strength	38 / 38	kV/mm	IEC 60243-1
^[C] Comparative tracking index	- / 600	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	2.7 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.2 / *	%	Sim. to ISO 62
^[C] Density	1040 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Other Extrusion

Delivery form

Granules, Black

Special Characteristics

Light stabilized or stable to light, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa