

Product Texts

HiDura D1X NT is a low-medium viscosity PA612 grade. It is suitable for monofilament, film and general purpose injection molding applications. It exhibits low moisture absorption, good chemical resistance, dimensional stability and high impact resilience. PA612 offers a unique balance of thermal, mechanical and physical properties.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	2.0 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2200 / 1500	MPa	ISO 527
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	3.6 / 7.5	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	3.3 / 5.2	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	218 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	53 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	136 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Electric strength	30 / 30	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	0.4 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.3 / *	%	Sim. to ISO 62
^[C] Density	1060 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding, Profile Extrusion, Sheet Extrusion, Other Extrusion, Casting

Delivery form

Pellets, Natural Color

Chemical Resistance

General Chemical Resistance

Applications

General Purpose, Monofilament

Regional Availability

North America, Europe, Asia Pacific