

Product Texts

PA612, 30% glass fibre reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring high stiffness and good mechanical resistance in direct contact with drinking water and food. Exhibits good dimensional stability, improved hydrolytic stability and very good chemical resistance to disinfectants. Product developed for applications in civil and industrial water management as well as appliances.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	8800 / 7900	MPa	ISO 527
^[C] Stress at break	165 / 130	MPa	ISO 527
^[C] Strain at break	3.4 / 4.1	%	ISO 527
^[C] Charpy impact strength, +23°C	70 / 80	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	13 / 15	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	210 / *	°C	ISO 11357-1/-3
^[C] Coeff. of linear therm. expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	120 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	1.9 / *	%	Sim. to ISO 62
^[C] Humidity absorption	0.7 / *	%	Sim. to ISO 62
^[C] Density	1290 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Granules, Natural Color

Additives

Release agent

Special Characteristics

Heat stabilized or stable to heat

Chemical Resistance

Hydrolytically Stable

Certifications

Food contact, Drinking water contact

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Other text information**Injection molding**

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
260 - 290°C

Mold Temperature
80 - 90°C

Injection Speed
medium