

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0075	mm/mm	ASTM D 955
Mechanical properties			
	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	114 / -	MPa	ASTM D 638
Elongation at Break	1.5 / -	%	ASTM D 638
Flexural Modulus	4830 / -	MPa	ASTM D 790
Flexural Strength	169 / -	MPa	ASTM D 790
Rockwell Hardness	M 95 /	-	ASTM D 785
Izod Impact notched, 1/8 in	53 / -	J/m	ASTM D 256
Thermal properties			
	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.5	mm	-
DTUL @ 264 psi	241	°C	ASTM D 648
Other properties			
	Value	Unit	Test Standard
Density	1240	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets, Black

Applications

Automotive

Additives

Lubricants

Regional Availability

North America

Special Characteristics

Heat stabilized or stable to heat