

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	32	g/10min	ASTM D 1238
Temperature	275	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.005	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	93.1	MPa	ASTM D 638
Elongation at Break	6	%	ASTM D 638
Flexural Modulus	4033	MPa	ASTM D 790
Flexural Strength	157	MPa	ASTM D 790
Izod Impact notched, 1/8 in	165	J/m	ASTM D 256
Izod Impact notched, Low-Temperature	90.7	J/m	ASTM D 256
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	260	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1180	kg/m ³	ASTM D 792

Characteristics

Delivery form

Natural Color

Special Characteristics

High impact or impact modified

Certifications

RoHS compliant

Regional Availability

Europe, Asia Pacific