

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.004</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>134 / -</b>	MPa	ASTM D 638
Elongation at Break	<b>2 / -</b>	%	ASTM D 638
Flexural Modulus	<b>5860 / -</b>	MPa	ASTM D 790
Flexural Strength	<b>179 / -</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>53 / -</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>1.5</b>	mm	-
DTUL @ 264 psi	<b>243</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1270</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Delivery form**

Pellets, Black

**Special Characteristics**

Heat stabilized or stable to heat

**Additives**

Lubricants

**Regional Availability**

North America