

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0075	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	130	MPa	ASTM D 638
Elongation at Break	3.5	%	ASTM D 638
Flexural Modulus	5300	MPa	ASTM D 790
Flexural Strength	190	MPa	ASTM D 790
Izod Impact notched, 1/8 in	60	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
DTUL @ 264 psi	238	°C	ASTM D 648
Melting Temperature	257	°C	ASTM D 3418
Other properties			
Density	1290	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	70 - 120	°C	-

Characteristics

Processing

Injection Molding, Other Extrusion

Regional Availability

North America, Europe, South and Central America

Delivery form

Natural Color