

**PA66-RG201**

PA66-GF20

Kingfa Sci. &amp; Tech.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.008</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>135</b>	MPa	ASTM D 638
Elongation at Break	<b>2.2</b>	%	ASTM D 638
Flexural Modulus	<b>6800</b>	MPa	ASTM D 790
Flexural Strength	<b>185</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 119</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>81.7</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-
DTUL @ 66 psi	<b>255</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>246</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Volume Resistivity	<b>1E15</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Water Absorption, 24hr	<b>0.6</b>	%	ASTM D 570
Density	<b>1410</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Injection Molding

**Applications**

Electrical and Electronical

**Delivery form**

Pellets

**Regional Availability**

Asia Pacific

**Special Characteristics**

Flame retardant