

**Product Texts**

Vydyne R525J BK0722 is a black, 25% glass filled, high flow, PA66 that contains an electrically neutral heat stabilizer. It is specifically designed for electrical applications requiring high dielectric strength, low conductivity, corrosion resistance, and laser markability.

**Processing/Physical Characteristics**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

**Mechanical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	8600 / 5500	MPa	ISO 527
<sup>[C]</sup> Stress at break	161 / 117	MPa	ISO 527
<sup>[C]</sup> Strain at break	2.4 / 7	%	ISO 527
Flexural modulus, 23°C	7700 / 5700	MPa	ISO 178
Flexural strength	250 / 150	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	65 / 67	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	55 / 66	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	11 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	10 / 10	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	10 / 15	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	9 / 10	kJ/m <sup>2</sup>	ISO 180/1A
	-30	°C	-

[C]: CAMPUS

**Thermal properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	245 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	258 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	25 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	109 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn. Thickness tested	HB / *	class	IEC 60695-11-10
	1.5 / *	mm	-
<sup>[C]</sup> Burning Behav. at thickness h Thickness tested	HB / *	class	IEC 60695-11-10
	0.8 / *	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

[C]: CAMPUS

**Electrical properties**

	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E11 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	27 / 24	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112
<b>ASTM Data</b>			
Arc Resistance	150 / -	s	ASTM D 495

[C]: CAMPUS

**Other properties**

	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	0.9 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1320 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	280 - 310	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	280 - 310	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Additives**

Release agent

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Laser Markable

**Chemical Resistance**

General Chemical Resistance

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

North America, Europe, Asia Pacific