

Product Texts

Vydyne RF005Z is a 25% glass fiber reinforced PA66 extrusion resin.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Stress at break	150 / -	MPa	ISO 527
^[C] Strain at break	2.8 / -	%	ISO 527

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	232 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1320 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing
Profile Extrusion

Additives
Lubricants

Delivery form
Pellets

Regional Availability
North America, Europe, Asia Pacific