

**AKROMID® A3 GF 30 7 S3 black (5393)**

PA66-GF30

Akro-Plastic GmbH

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>9000 / 5000</b>	MPa	ISO 527
Stress at break	<b>165 / 100</b>	MPa	ISO 527
Strain at break	<b>3.6 / 7.2</b>	%	ISO 527
Charpy impact strength, +23°C	<b>90 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>18 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>262 / *</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>235 / *</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>255 / *</b>	°C	ISO 75-1/-2

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1330 / -</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Melt temperature	<b>320</b>	°C	-
Mold temperature	<b>100</b>	°C	-
Injection pressure	<b>75</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Features**

Good Adhesion

**Delivery form**

Black

**Applications**

Automotive

**Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe, Asia Pacific