

Product Texts

Base Polymer	Polyamide 66
Filler/Additive System	30 % glass fibres
Special Features	heat stabilised,high surface gloss
Market Segment	various
Application Area	various

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

[C] Tensile Modulus	10000 / 6300	MPa	ISO 527
[C] Stress at break	180 / 118	MPa	ISO 527
[C] Strain at break	3 / 5.6	%	ISO 527
[C] Charpy impact strength, +23°C	80 / 85	kJ/m ²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	10 / 13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

[C] Temp. of deflection under load, 1.80 MPa	255 / *	°C	ISO 75-1/-2
--	---------	----	-------------

[C]: CAMPUS

Other properties

dry / cond

Unit

Test Standard

[C] Density	1360 / -	kg/m ³	ISO 1183
-------------	----------	-------------------	----------

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Special Characteristics

Heat stabilized or stable to heat

Other text information**Injection molding**

Pre-Drying Conditions	in a dry air (dessiccant) dryer <80 °C for 2-12 h dependant on moisture content max. moisture content <0,15 %
Processing Injection Moulding	melt temperature 280-300 °C mould temperature 80-120 °C
Storage	dry, protected from light not above 30°C