

BALTAMID 6.6 GF 30 schwarz

PA66-GF30

BALTIC Kunststoff Handels GmbH

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	140	MPa	ISO 527
ASTM Data			
Elongation at Break	3	%	ASTM D 638
Flexural Modulus	6500	MPa	ASTM D 790
Izod Impact notched, 1/8 in	65	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Melting Temperature	255	°C	ASTM D 3418
Vicat Temperature	225	°C	ASTM D 1525
Other properties			
Density	1360	kg/m ³	ASTM D 792
Moisture Content	0.2	%	-

Characteristics**Processing**

Injection Molding

Additives

Release agent

Delivery form

Black

Regional Availability

Europe