

**Product Texts**

LNP LUBRICOMP RFN16 compound is based on Nylon 6/6 resin containing 30% glass fiber and Molybdenum diSulfide (MoS<sub>2</sub>). Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E207780-103093658](https://www.ulprospector.com/usa/Products/PA66-GF30)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.3	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	9560	MPa	ASTM D 638
Tensile Strength at Break	155	MPa	ASTM D 638
Elongation at Break	2.9	%	ASTM D 638
Flexural Modulus	7130	MPa	ASTM D 790
Flexural Strength	206	MPa	ASTM D 790
Izod Impact notched, 1/8 in	112	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	1000	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
<b>ASTM Data</b>			
DTUL @ 264 psi	205	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1410	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	265 - 275	°C	-
Mold temperature	80 - 95	°C	-
Zone 1	250 - 260	°C	-
Zone 2	265 - 275	°C	-
Zone 3	275 - 290	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.3 - 0.7	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

Asia Pacific