

Product Texts

30% Glass Reinforced, Heat Stabilized

ISO 1043 PA66-GF30

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	15 / *	cm ³ /10min	ISO 1133
Temperature	280 / *	°C	-
Load	2.16 / *	kg	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9700 / 6500	MPa	ISO 527
^[C] Stress at break	170 / 130	MPa	ISO 527
^[C] Strain at break	2.6 / 4	%	ISO 527
^[C] Charpy impact strength, +23°C	80 / 110	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11 / 13	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	244 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Relative permittivity, 1MHz	4 / -	-	IEC 62631-2-1
^[C] Dissipation factor, 1MHz	190 / -	E-4	IEC 62631-2-1
^[C] Volume resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 4E14	Ohm	IEC 62631-3-2
^[C] Electric strength	26 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	550 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	1.7 / *	%	Sim. to ISO 62
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets, Natural Color

Regional Availability

Asia Pacific

Other text information**Injection molding**[Steel recommendations for molds screws and barrels](#)[Trouble shooting guideline for injection molding](#)