

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.003</b>	mm/mm	ASTM D 955

Mechanical properties	dry / cond	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>9700 / 7000</b>	MPa	ASTM D 638
Tensile Strength	<b>200 / 135</b>	MPa	ASTM D 638
Elongation at Break	<b>3.2 / 5</b>	%	ASTM D 638
Flexural Modulus	<b>12200 / 6500</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>140 / 110</b>	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	<b>950 / 970</b>	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
DTUL @ 66 psi	<b>260</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>250</b>	°C	ASTM D 648
Melting Temperature	<b>260</b>	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	<b>1.9</b>	%	ASTM D 570
Density	<b>1370</b>	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	<b>90</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>270 - 285</b>	°C	-
Mold temperature	<b>80 - 90</b>	°C	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

U.V. stabilized or stable to weather

### Delivery form

Natural Color

### Regional Availability

North America, Europe, South and Central America