

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0025</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Modulus	<b>10300</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>183</b>	MPa	ASTM D 638
Elongation at Break	<b>2.5</b>	%	ASTM D 638
Flexural Modulus	<b>9650</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>270</b>	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	<b>1400</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>249</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>1370</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Delivery form**

Pellets

**Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa