

**Product Texts**

PA66 flame retardant injection moulding grade, 30% glass fibre reinforced. Halogen and red phosphorus free, improved fluidity. Electrical light grey colour.

Suitable for parts requiring fire retardancy along with high stiffness and good mechanical resistance. Good electrical insulating properties. Rated V-0 according to UL-94.

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>10400 / -</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>135 / -</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>2.3 / -</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>50 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>8 / -</b>	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>258 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>240 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>255 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at thickness h	<b>V-0 / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
Yellow Card available	<b>yes / *</b>	-	-

[C]: CAMPUS

<b>Electrical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	<b>1E13 / 1E11</b>	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Surface resistivity	<b>* / 1E10</b>	Ohm	IEC 62631-3-2
<sup>[C]</sup> Comparative tracking index	<b>600 / -</b>	-	IEC 60112

[C]: CAMPUS

<b>Other properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Water absorption	<b>5.5 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	<b>1.3 / *</b>	%	Sim. to ISO 62
<sup>[C]</sup> Density	<b>1440 / -</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Granules

**Additives**

Release agent

**Special Characteristics**

Flame retardant, Halogen-free, Phosphorus-free, Heat stabilized or stable to heat

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

**Other text information**

**Injection molding**

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.10%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Avoid excessive shear rates and high thermal stresses for better processing. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature

275 - 290°C

Mold Temperature

80 - 90°C

Injection Speed

medium-high