

**RESTRAMID A27 GF30 BK 1A0000**

PA66-GF30

Polimarky Spółka Jawna

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	- / <b>6000</b>	MPa	ISO 527
Strain at break	- / <b>5</b>	%	ISO 527
<b>Other properties</b>			
Density	- / <b>1350</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Delivery form**

Black

**Regional Availability**

Europe