

**RTP PA66 30 GF FRO BLK**

PA66-GF30

RTP Company

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.00225</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>10340</b>	MPa	ASTM D 638
Tensile Strength	<b>145</b>	MPa	ASTM D 638
Flexural Modulus	<b>11030</b>	MPa	ASTM D 790
Flexural Strength	<b>234</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>96.1</b>	J/m	ASTM D 256

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-0</b>	-	UL 94
Thickness tested	<b>0.794</b>	mm	-
DTUL @ 264 psi	<b>232</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water Absorption, 24hr	<b>0.6</b>	%	ASTM D 570
Density	<b>1650</b>	kg/m <sup>3</sup>	ASTM D 792
Moisture Content	<b>0.2</b>	%	-

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>79.4</b>	°C	-
Pre-drying - Time	<b>4</b>	h	-
Melt temperature	<b>277 - 299</b>	°C	-
Mold temperature	<b>65.6 - 107</b>	°C	-
Injection pressure	<b>68.9 - 124</b>	MPa	-

**Characteristics****Processing**

Injection Molding

**Special Characteristics**

Flame retardant

**Delivery form**

Black

**Regional Availability**

North America, Europe, Asia Pacific