

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9500 / 5200	MPa	ISO 527
^[C] Stress at break	130 / 70	MPa	ISO 527
^[C] Strain at break	2.6 / 10	%	ISO 527
^[C] Charpy impact strength, +23°C	35 / 65	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	30 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	4 / 6	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	3 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

Europe