

Taromid A 280 H G6 DX0 TR1

PA66-GF30

Taro Plast S.p.A.

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9400	MPa	ISO 527
Stress at break	145	MPa	ISO 527
Strain at break	2.2	%	ISO 527
Flexural modulus, 23°C	9200	MPa	ISO 178
Charpy impact strength, +23°C	32	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
ASTM Data			
Izod Impact notched, 1/8 in	80	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	253	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Vicat softening temperature, B	242	°C	ISO 306
Coeff. of linear therm. expansion, parallel	25	E-6/K	ISO 11359-1/-2
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	35	%	ASTM D 2863

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	26	kV/mm	IEC 60243-1
Comparative tracking index	400	-	IEC 60112

Other properties	Value	Unit	Test Standard
Water absorption	4.5	%	Sim. to ISO 62
Density	1570	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

Regional Availability

Europe

Features

Low Odor