

**Product Texts**

Impact- modified polyamide 6.6 with 30 % glass fiber reinforcement.

For molded parts with stiffness and cold impact resistance.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>8000</b>	MPa	ISO 527
Stress at break	<b>140</b>	MPa	ISO 527
Strain at break	<b>3.7</b>	%	ISO 527
Charpy impact strength, +23°C	<b>85</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>25</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	<b>225</b>	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	<b>245</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>HB</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Water absorption	<b>4</b>	%	Sim. to ISO 62
Humidity absorption	<b>1.4</b>	%	Sim. to ISO 62
Density	<b>1260</b>	kg/m <sup>3</sup>	ISO 1183

<b>Processing Recommendation Injection Molding</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Pre-drying - Temperature	<b>80</b>	°C	-
Pre-drying - Time	<b>4 - 8</b>	h	-
Processing humidity	<b>≤0.1</b>	%	-
Mold temperature	<b>40 - 80</b>	°C	-
Feed temperature	<b>60 - 80</b>	°C	-
Zone 1	<b>260 - 290</b>	°C	-
Nozzle temperature	<b>270 - 300</b>	°C	-
Maximum residence time	<b>8</b>	min	-

**Characteristics****Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

High impact or impact modified, Heat stabilized or stable to heat

**Regional Availability**

Europe