

Product Texts

Vydyne A 30 GF NT WR is standard flow, 30% glass-fiber reinforced PA66 resin. Suitable for use with water up to 85 C, this product is also lubricated for improved machine feed and flow.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	9800 / -	MPa	ISO 527
^[C] Stress at break	185 / -	MPa	ISO 527
^[C] Strain at break	2.5 / -	%	ISO 527

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	245 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Humidity absorption	1.7 / *	%	Sim. to ISO 62
^[C] Density	1360 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific