

**Product Texts**

Vydyne R530H BK0202 is a recycled, 30% glass-filled, heat-stabilized, high viscosity PA66 based resin designed for injection molding applications. R530H BK0202 offers standard flow with a black surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	10000 / 7400	MPa	ISO 527
<sup>[C]</sup> Stress at break	195 / 135	MPa	ISO 527
<sup>[C]</sup> Strain at break	3 / 5	%	ISO 527
Flexural modulus, 23°C	9600 / 6000	MPa	ISO 178
Flexural strength	270 / 190	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	75 / 85	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	65 / 80	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	11 / 13	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	10 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	12 / 13	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	10 / 11	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	22 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	107 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-
Glow Wire Flammability Index (GWFI)	675	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.75	mm	-
Glow Wire Flammability Index (GWFI)	675	°C	IEC 60695-2-12
GWFI - thickness tested (2)	1.5	mm	-
Glow Wire Flammability Index (GWFI)	675	°C	IEC 60695-2-12
GWFI - thickness tested (3)	3	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.75	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (2)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	700	°C	IEC 60695-2-13
GWIT - thickness tested (3)	3	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	0.75	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E11 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	20 / -	kV/mm	IEC 60243-1

[C] Comparative tracking index	325 / -	-	IEC 60112
--------------------------------	---------	---	-----------

**ASTM Data**

Arc Resistance	90 / -	s	ASTM D 495
----------------	--------	---	------------

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	0.9 / *	%	Sim. to ISO 62
[C] Humidity absorption	1.9 / *	%	Sim. to ISO 62
[C] Density	1370 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	280 - 310	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	280 - 310	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Black

**Additives**

Lubricants

**Special Characteristics**

Heat stabilized or stable to heat

**Features**

Fatigue Resistance

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance, Hydrolytically Stable, Oil Resistance

**Certifications**

Recycled Resin Content

**Applications**

Automotive

**Regional Availability**

North America, Europe, Asia Pacific