

Product Texts

Vydyne R530J NT0724 is a natural, 30% glass filled, high flow, PA66 that is heat stabilized with an electrically neutral heat stabilizer. It is specially designed for electrical applications requiring high dielectric strength, low conductivity, and corrosion resistance.

Processing/Physical Characteristics

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.4 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	0.9 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10000 / 7400	MPa	ISO 527
^[C] Stress at break	195 / 135	MPa	ISO 527
^[C] Strain at break	3 / 5	%	ISO 527
Flexural modulus, 23°C	9600 / 6000	MPa	ISO 178
Flexural strength	270 / 190	MPa	ISO 178
^[C] Charpy impact strength, +23°C	75 / 85	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	65 / 80	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	11 / 13	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	10 / 11	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	12 / 13	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	10 / 11 -30	kJ/m ² °C	ISO 180/1A -

[C]: CAMPUS

Thermal properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	250 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	260 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	22 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	107 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn. Thickness tested	HB / * 1.5 / *	class mm	IEC 60695-11-10 -
^[C] Burning Behav. at thickness h Thickness tested	HB / * 0.8 / *	class mm	IEC 60695-11-10 -
ASTM Data			
UL 94 Flame rating Thickness tested	HB 0.75	- mm	UL 94 -

[C]: CAMPUS

Electrical properties

	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E11 / -	Ohm*m	IEC 62631-3-1
^[C] Electric strength	24 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600 / -	-	IEC 60112
ASTM Data			
Arc Resistance	150 / -	s	ASTM D 495

[C]: CAMPUS

Other properties

	dry / cond	Unit	Test Standard
^[C] Water absorption	0.9 / *	%	Sim. to ISO 62
^[C] Humidity absorption	1.9 / *	%	Sim. to ISO 62
^[C] Density	1370 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	280 - 310	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	280 - 310	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Release agent

Special Characteristics

Heat stabilized or stable to heat

Features

Laser Markable

Chemical Resistance

General Chemical Resistance

Applications

Automotive, Electrical and Electronical

Regional Availability

North America, Europe, Asia Pacific