

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0035	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	155	MPa	ASTM D 638
Elongation at Break	3.5	%	ASTM D 638
Flexural Modulus	8270	MPa	ASTM D 790
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Melting Temperature	260	°C	ASTM D 3418
Electrical properties			
ASTM Data			
Volume Resistivity	1E15	Ohm*cm	ASTM D 257
Other properties			
Density	1360	kg/m ³	ASTM D 792
Moisture Content	0.25	%	-

Characteristics

Delivery form

Pellets, Natural Color

Regional Availability

North America

Additives

Lubricants