

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	11500	MPa	ISO 527
^[C] Stress at break	165	MPa	ISO 527
^[C] Strain at break	2.1	%	ISO 527
^[C] Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	238	°C	ISO 75-1/-2

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1390	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Delivery form
Black

Certifications
Recycled Resin Content