

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0055	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	128	MPa	ASTM D 638
Tensile Strength at Break	128	MPa	ASTM D 638
Flexural Modulus	6895	MPa	ASTM D 790
Izod Impact notched, 1/8 in	133	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	260	°C	ASTM D 648
DTUL @ 264 psi	243	°C	ASTM D 648
Other properties			
Density	1350	kg/m ³	ASTM D 792
Processing Recommendation Injection Molding			
Pre-drying - Temperature	73.9 - 85	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	288 - 299	°C	-
Mold temperature	65.6 - 104	°C	-
Zone 1	293 - 304	°C	-
Zone 2	277 - 288	°C	-
Zone 3	271 - 282	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Lubricants

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America